

## WIL-1 No-Clean Liquid Flux

### Introduction

WIL-1 is a low activity VOC free no-clean liquid flux for selective and wave solder applications. WIL-1 is compatible with spray, foaming, and drop-jet type flux systems. WIL-1 works well with leaded and lead-free alloys and is halide free.

### Attributes

- VOC free liquid flux for wave and selective soldering. 0.0 g/L VOC.
- Works well for Sn63/Pb37, SAC305 and SN100C alloys.
- Halide free formulation.

Liquid Flux Packaging	Part Number	Net Volume
Jug	WIL-1U	1 gallon
Pail	WIL-1P	5 gallons
Drum	WIL-1D	55 gallons

### Compatible Products

TK-100 Titration Kit is optional. Flux control is best done through specific gravity analysis.

### Storage and Handling

- Shelf life is 3 years when the unopened flux is stored between 50 to 90 °F (10 and 32 °C).
- Keep the flux sealed in the original container to limit evaporation of solvent and minimize the risk of contamination.
- When storing used flux, do not mix it into the container with the new (fresh) flux.

Flux Parameters	Preferred	Acceptable
Specific gravity	1.01 to 1.02 g/cc	1.00 to 1.03 g/cc
Acid number	42 - 48 mg KOH / gram flux	40 - 50 mg KOH / gram flux
Amount of flux (Foaming)	1000 - 1300 µg / in <sup>2</sup> of dried flux 14.3 - 18.6 mg / in <sup>2</sup> of wet flux	800 - 1500 µg / in <sup>2</sup> of dried flux 11.4 - 21.4 mg / in <sup>2</sup> of wet flux
Amount of flux (Spray)	800 - 1200 µg / in <sup>2</sup> of dried flux 11.4 - 17.1 mg / in <sup>2</sup> of wet flux	500 - 1500 µg / in <sup>2</sup> of dried flux 7.10 - 21.4 mg / in <sup>2</sup> of wet flux

Coverage of flux should be uniform over the entire fluxed area. Penetration of flux through the circuit board holes can be checked using paper or cardboard on top of the circuit board run through the fluxer. Inspect the paper or cardboard for uniform wetness at each hole. Make adjustments to the flux system if necessary.

Wave Solder Parameters	Sn63/Pb37	SN100C or SAC305
Immersion depth in wave	½ to ⅔ of the board thickness	½ to ⅔ of the board thickness

Top side preheat temperature	110 to 130 °C	120 to 140 °C
Bottom side preheat temperature	25 to 35 °C higher than the top side	25 to 35 °C higher than the top side
Preheat ramp rate maximum	2 °C / second maximum	2 °C / second maximum
Conveyor speed	4 to 6 ft/min (1.2 - 1.8 m/min)	3 to 6 ft/min (0.9 - 1.8 m/min)
Contact time in wave	2 to 4 seconds	3 to 6 seconds
Solder pot temperature	230 to 260 °C	250 to 275 °C

- These parameters are general guidelines. The optimum settings may be different depending upon the process, equipment, components and circuit boards.

Water based fluxes like WIL-1 require higher pre-heat settings than isopropanol-based fluxes in order to evaporate off the water completely before the circuit boards touch the molten solder. If water is left on the circuit boards then the molten solder will cause explosive vaporization resulting in solder splattering and other issues. Pre-heat should be set so that water-based fluxes are dry as the circuit boards exit the pre-heat section.

Selective Solder Parameters	Sn63/Pb37	SN100C or SAC305
Top side preheat temperature	110 to 130 °C	120 to 140 °C
Bottom side preheat temperature	25 to 35 °C higher than the top side	25 to 35 °C higher than the top side
Preheat ramp rate maximum	2 °C / second maximum	2 °C / second maximum
Movement rate while soldering	5 to 15 in/min	5 to 15 in/min
Contact time	1 to 3 seconds	1 to 4 seconds
Solder pot temperature	280 to 310 °C	290 to 320 °C

- These parameters are general guidelines. The optimum settings may be different depending upon the process, equipment, components and circuit boards.

<b>Flux Control</b>
---------------------

De-ionized water will evaporate slowly out of the flux over time and the solvent should be replaced through analysis and additions of de-ionized water. WIL-1 flux is best controlled through specific gravity analysis using the procedure below. The flux should be tested and thinned approximately once every 4 to 8 hours of operation (foaming systems), or once every 40 hours of operation (spray systems).

1. Measure the specific gravity of the flux at 68 - 72 °F.
2. Calculation for the addition of D.I. water:  

$$\text{D.I. water add (\% vol)} = \frac{[(\text{SG} - 1.02) / (\text{SG} - 1.00)] \times 100\%}{}$$

Maintain the specific gravity between 1.01 and 1.02 through additions of D.I. water. For example, if the specific gravity is 1.04 then the amount of D.I. water required would be 50% by volume. If the flux sump holds 20 gallons, then an addition of 10 gallons of D.I water would reduce the specific gravity from 1.04 to 1.02.

In recirculating flux equipment, the flux will accumulate contaminants and debris over time. Spent flux should be replaced after approximately 40 hours of use. The equipment, foam stone and sump should be cleaned with flux thinner before adding new (fresh) flux.

During extended shut down periods such as nights and weekends, the flux should be removed from the machine and stored in a sealed container. The air stone should be immersed in flux thinner during the shut-down period. Pumps and tubing should be flushed with flux thinner during the shut-down period.

**Cleaning**

Raw flux can be removed from circuit boards and equipment using flux thinner (D.I. water). After heating, no-clean flux residues are designed to be “safe” and do not need to be removed from the circuit board. If removal of the flux residues is desired, then D.I. water heated to 120 - 180 °F can be used in standard washing equipment.

**Safety**

Wear chemically resistant gloves and safety glasses when handling liquid flux. Avoid breathing fumes, especially during heating of the flux. Follow the guidelines in the Safety Data Sheet (SDS).

J-STD-004B Flux Standard	Test Method	Result
J-STD-004B classification	J-STD-004B methods	ORLO
Visual appearance	Visual	Clear to light yellow
Solids content	IPC 2.3.34	6.5 to 7.5% wt
Acid value	IPC 2.3.13	40 to 50 mg KOH / gram flux
Specific gravity	ASTM D-1298	1.01 to 1.02 g/cc
VOC content	Calculation	0.0 % wt (0.0 g/L)
Halide ion content (Br, Cl, F, I)	IPC 2.3.28.1	0.0 % wt
Halogen content (Br and Cl)	EN 14582, IPC 2.3.28.1	4.0 to 5.0 % wt of the solids
Halide by silver chromate	IPC 2.3.33	No halides detected
Fluoride by spot test	IPC 2.3.35.1	None detected
Copper mirror	IPC 2.3.32	Low activity
Copper corrosion	IPC 2.6.15	No corrosion
Surface Insulation Resistance (SIR) Comb-up	IPC 2.6.3.7	Pass > 1.00E+08 ohms
Surface Insulation Resistance (SIR) Comb-down	IPC 2.6.3.7	Pass > 1.00E+08 ohms
Electro Chemical Migration (ECM)	IPC 2.6.14.1	Pass

**Limited Liability and Warranty Disclaimer**

All information, statements, technical data, and recommendations contained in this Technical Data Sheet are based on testing we believe to be reliable. However, the accuracy or completeness thereof is not guaranteed. It is impossible for our lab to account for all manufacturing conditions and variables. Products are warranted to be free from defects at the time sold. To the full extent consistent with applicable law, the exclusive remedy of the user or buyer is to receive replacement product for any product defective at the time sold. FCT Assembly, Inc. makes NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Further, FCT Assembly, Inc. makes no other express, implied, or statutory warranties unless otherwise specified in writing and signed by officers of the corporation.